

Product Description

DM-15204S is a screen/stencil/syringe printed high thermal conductivity PCM (Phase Change Material) paste. It is designed to provide superior heat transfer between a heat generating component eg power device and heat sink, heat spreader or other cooling device eg fans, heat pipes. The paste incorporates a PCM additive that softens at ~55°C to fill interface voids and cavities to provide low thermal interface resistance by elimination of air filled gaps and improving heater transfer at the interface.

Product Benefits

- Non-silicone (no migration, leach-out or contamination)
- Use of PCM additives provides excellent thermal transfer at interface by removal of air filled voids.
- Electrically insulative
- Excellent thermal conductivity (4 W/m.K)
- Excellent durability (150°C, bake test)
- Stencil/screen printed enabling reduced bond-line thickness (<45 µm) due to small particle filler size, reworkable. Syringe packaging also available

Applications

Interface for semiconductors requiring low pressure or spring clamp mounting. Consumer electronics, Set-top boxes, IP routers, ECUs Memory and Power modules. CPU to Heat sink, Transistors, Diodes, IGBTs, Rectifiers, LED. TEC modules, Telecommunication hardware and as a gap filler for battery systems.

Deposition Properties

Test	Properties
Viscosity before Phase Change (Pa.s) (Lamy Cone & Plate, 50s ⁻¹ , 25°C)	8 - 12 (screen/stencil), 20-40 (Syringe)
Colour	Grey
Density	2.2 - 2.4 g/cm ³
PCM Softening Temperature	~55°C

Physical Properties

Screen/Stencil	Properties
Print method	Flood-print
Print Speed	100 mm/s
Print Gap	1.5 mm
Squeegee Pressure	~10 Kg
Squeegee	70A Shore Hardness
Screen	Aperture: 90µm Wire: 40µm Mesh: 77T/cm Emulsion: 5µm
Recommended Drying Conditions	125°C (10 mins), 80°C (150 mins), 22°C (24 hrs)
Typical Minimum Bondline thickness	35-40 µm
Print Resolution	250 µm (Line/Space)

Syringe	Properties
Syringe Flow Rate	63 g/min (@90psi)
Recommended Drying Conditions	No Dry

Thermal/Electrical Properties

Parameter	Properties
Thermal Conductivity (ASTM D5470)	4 W/m.K
Thermal Contact Resistance (ASTM D5470)	$7.5 \times 10^{-5} \text{ m}^2\text{.K/W}$
Volume Resistivity (ASTM D257)	$8.4 \times 10^{14} \text{ } \Omega\text{.cm}$
Dielectric Constant (1 KHz) (ASTM D149)	6.7
Dielectric Strength (ASTM D149 MOD)	>2.4 kV/mm

Durability Performance

Parameter	Properties
Thermal Stability (150°C, bake test)	1000 hours
Operating Temperature Range	150°C

The product is RoSH compliant.

Storage and shelf-life

The paste shelf-life is 24 months from date of shipment. Dycotec Materials cannot assume responsibility for a paste that has not been stored in appropriate conditions or where the pastes have been contaminated following use.

Safety and Handling

For safe use of this product, please review relevant material and safety datasheet (MSDS).

Packaging

DM-TIM-15204S is provided in a pot. Package sizes of 250g, 1 Kg and 5 Kg are available.

DM-TIM-15204-SY-30 (30cc) or 50cc syringes eg DM-TIM-15204-SY-XX (where XX = 30 or 50). Larger syringe sizes available on request.

For more information, please contact:

Dycotec Materials Ltd
Unit 6, Stainer Road
Porte Marsh Industrial Estate
Calne, Wiltshire, SN11 9PX, UK
Email: Info@dycotecmaterials.com
Tel: +44 (0)1793 422598
www.dycotecmaterials.com

All information reported in the datasheet is for experimental work undertaken in our laboratories and illustrates typical values only. Processing conditions may vary depending on customers' experience and their application requirements and manufacturing process equipment set-up.

Note: The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Dycotec Materials specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale of use of Dycotec Material's products. Dycotec Materials specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits. The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Dycotec Material patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one of or more UK or foreign patents or patent applications.

Copyright© 2022

Revision: 1.00

Date: January-2022