



RockeTape™ Product Specifications

Property	Units	Test Method	RTAZS-025100	RTPIS-025100	RTGRS-025100	RTVDAS-025100
Thickness	mil	In-house	7.5 ± 1.5	9.5 ± 1.5	10.5 ± 1.5	9.5 ± 1.5
Density	g/cm ³	In-house	0.38 ± 0.05	0.58 ± 0.05	0.70 ± 0.05	0.60 ± 0.05
Thermal Conductivity	W/m-K	ASTM C518-21	0.038 ± 0.003	0.046 ± 0.003	0.053 ± 0.005	0.046 ± 0.003
72 hr Peel strength	N/m	ASTM D3330	≥ 300	≥ 200	*nm	≥ 200
Width	Inches	-	1 (min. 0.9375)	1 (min. 0.9375)	1 (min. 0.9375)	1 (min. 0.9375)
Length	Feet	-	25 (min. 24.75)	25 (min. 24.75)	25 (min. 24.75)	25 (min. 24.75)

*nm (not measurable)